

ARBOFLEX® PU THICKENER

ARBOFLEX PU THICKENER ADDITIVE FOR THICKENING ARBOFLEX PU MEMBRANES

ARBOFLEX PU THICKENER is a polymeric thickener, developed specifically as a liquid additive for the polyurethane liquid membrane ARBOFLEX PU. For use on vertical or sloped surfaces, providing thixotropic properties.

PRODUCT APPLICATION

- Additive for ARBOFLEX PU to be applied on vertical or sloped surfaces. Prevent sagging of the membrane due to its drying time.

APPLICATION METHOD

- Add ARBOFLEX® PU THICKENER in the proportion needed (maximum 800 ml per 20 kg of ARBOFLEX PU) in the drum of the ARBOFLEX PU.
- The mixing ratio is relative to site conditions.
- Continue mixing until the product is homogeneous.
- If the outside temperature is lower than 5°, heat before mixing with ARBOFLEX PU.

maximum consumption	800 ml per 20 kg of ARBOFLEX PU
---------------------	---------------------------------

density at 25°C	0.9 g/cm ³
-----------------	-----------------------



SHELF LIFE

12 months at temperatures between 5° C and 35° C, provided it is stored in a dry place.

PACKAGING

Metal tins of 1l.

HANDLING

The safety recommendations are necessary for correct installation of the product.

- Respiratory Protection: When handling or spraying use an air-purifying respirator.
- Skin protection: Use rubber gloves, remove immediately after contamination. Wear clean protective overalls. Wash thoroughly with soap and water after working.
- Eye / Face: Wear safety goggles to prevent splashing and exposure to particles in the air.
- Waste generation should be avoided or minimized. Incinerate under controlled conditions in accordance with local laws and national regulations.

For further information consult our technical department.

PROPERTIES

PROPERTIES	VALUES
Density at 23 °C ISO 1675	±0.9 g/cm ³
Solids content ISO 1768	±26%
Viscosity at 23 °C ISO 2555	20~50 cps

Both the information and the product descriptions contained in this publication have been compiled to the best of our knowledge and belief based on our prior experiences and tests. Claims for compensation may not be derived from the same. We reserve the right to make improvements to our product range, in accordance with our high standards in relation to technical advancement and the progression of quality.



CARLISLE® Construction Materials Ltd.
Lancaster House | Concorde Way
Millennium Business Park | Mansfield

United Kingdom
Nottinghamshire | NG19 7DW
United Kingdom

T +44(0)1623 62 72 85
F +44(0)1623 65 27 41

E info.uk@ccm-europe.com
www.ccm-europe.com

