

Tecnatorch Sand

Torch On Sanded Capsheet

Tecnatorch Sand is a polyester reinforced SBS-modified bitumen membrane.

APPLICATION

Tecnatorch Sand is intended for use as a torch-applied top sheet or underlay in a bitumen built-up roof system. Membranes should be installed in accordance with the manufacturer's guidelines.

Upper Surface	Silica sand with thermofusible film to overlap selvedge
Lower Surface	Thermofusible PE film
Material	SBS-Modified Bitumen
Type of Reinforcement	Polyester 195g/m ²

Characteristic	Test Method	Value or Statement	Tolerance	Units
Length	EN 1848-1	8	±0.1	m
Width (inc. Selvedge)	EN 1848-1	1	±0.02	m
Mass per unit area	BS EN 1849-1	4.5	±0.15	kg.m ²
Effective thickness	BS EN 1849-1	3.8	±0.2	mm
Water tightness	BS EN 1928 (B)	Pass	-	-
External fire performance*	BS EN 13501-5	B _{ROOF} (t4)	-	-
Tensile strength	BS EN 12311-1	900 (MD); 900 (TD)	±35%	N/50 mm
Elongation	BS EN 12311-1	35 (MD); 35 (TD)	±35%	%
Dimensional stability	BS EN 1107-1	≤ 1	-	%
Flexibility at low temperature	BS EN 1109	≤ -15	-	°C
Flow resistance at elev. temp	BS EN 1110	> 90	-	°C

MD = Machine Direction. TD = Transverse Direction.

PACKAGING

Description	Roll Dimensions	Rolls per pallet	Product Code
Tecnatorch Sand	8m x 1m	25	10001252

STORAGE

Materials for reinforced bitumen membrane roofing should be stored upright on clean dry level surfaces, undercover and clear of the ground. The same protection should be given to materials temporarily kept outdoors or on the roof during construction. Storage temperatures should be between 0°C and 30°C. Refer to BS 8000-4 (Section 2.1.2.2) for further information.

INSTALLATION SUMMARY

Tecnatorch Sand membranes are applied by torch-on application. The membrane is to be installed in accordance with current and relevant standards such as BS 8217, BS 6229 and BS 8000-4.

For further details please consult our Flat Roofing Product Installation Guidelines or contact our BMI Icopal technical services team.

TECHNICAL SERVICES

For further information and technical support, please contact our technical services team:

T: +44 (0) 330 123 4585

E: technical.uk@bmigroup.com

CERTIFICATION

Tecnatorch Sand has been independently site and laboratory tested by the British Board of Agrément, and awarded BBA certificate number 07/4409 (PS4).



SAFETY, QUALITY & ENVIRONMENT

BMI Icopal membranes are manufactured under a Quality Management System approved to ISO 9001: 2015 and an Environmental Management System approved to ISO 14001: 2015 by TÜV NORD CERT GmbH.

Information regarding transportation, handling, storage and disposal can be found on the relevant Safety Data Sheet.



ISO 9001:2015
44 100 21410102



ISO 14001:2015
44 100 21410102



BMI Group UK Limited

BMI House, 2 Pitfield, Kiln Farm, Milton Keynes, MK11 3LW
bmigroup.com/uk

Product, technical standards and codes of practice are under constant review. We reserve the right to change and amend products and information without prior notice. For the latest information, suitability and specification advice, please contact BMI Icopal technical services team.